



BARI



Specification in according EN 1307

Costruzione	Technique de fabrication	Construction	Herstellungsverfahren
Tufting velluto 1/10"	Tufted velours 1/10"	Tufted cut pile 1/10"	Getufted Velours 1/10"
Composizione	Composition du velours	Pile composition	Polnutschicht
100% poliammide	100% polyamide	100% polyamid	100% polyamid
Sottofondo	Dossier	Secondary backing	Rückenausrüstung
Juta sintetica	Jute synthétique	Synthetic jute	SDR Textilrücken
Punti al m²	Touffes au m²	Stitches per m²	Knoten m²
± 146150	± 146150	± 146150	± 146150
Altezza pelo	Hauteur du velours	Pile height	Polhöhe
± 8.1 mm	± 8.1 mm	± 8.1 mm	± 8.1 mm
Altezza totale	Hauteur totale	Total height	Gesamtdicke
± 10.5 mm	± 10.5 mm	± 10.5 mm	± 10.5 mm
Peso della fibra	Poids du velours	Yarn weight	Polgewicht
± 1050 g/m²	± 1050 g/m²	± 1050 g/m²	± 1050 g/m²
Peso totale	Poids total	Total weight	Gesamtgewicht
± 1970 g/m²	± 1970 g/m²	± 1970 g/m²	± 1970 g/m²
Larghezza rotolo	Largeur du rouleau	Roll width	Breite
400 cm	400 cm	400 cm	400 cm
Famiglia Tufting 1	Famiglia Tufting 1	Famiglia Tufting 1	Famiglia Tufting 1



Colour fastness to light	5 (4 pastel shade)	Thermal resistance m² K/W	0,17
Insulation impact noise Lw	29 dB	Body voltage walking test kV	2
Acoustical absorption α _w	0,20		

RESISTENZA – WEARABILITY RESISTANCE - STRAPAZIERWERT				COMFORT – COMFORT CONFORT - KOMFORTWERT			
estrema extreme extrême extrem	elevata high élevée stark	normale good normale normal	sufficiente normal suffisante gering	medio medium moyen einfach	buono good bon gut	alto very good élevé hoch	ottimo excellent excellent luxuriös

Approved by Technique Management: M. Medica

Date: 20/11/2012